



Dramix® Loop™

Steel fibres with near-zero carbon emissions for more sustainable concrete structures.

Ultra dense fibre network

100% circular

EPD of 0,0436

High strength

From the world's leading steel cord manufacturer, reinforcing 1 in every 4 tyres, comes a solution that minimises CO₂. This takes the form of Dramix® Loop™, ready to tackle this challenge by transforming tyre cord from end-of-life tyres into high-performance steel fibres.

As such, the prioritisation of finding a circular use for this high-grade steel resulted in the first high-performing steel fibre - specifically engineered for concrete reinforcement,

supporting a truly circular economy with near-zero carbon emissions.

What sets Dramix® Loop™ apart is its very low contamination percentage, high tensile strength, and strict production tolerances. This ensures higher precision, and reliable performance in non-structural concrete applications e.g. precast & flooring applications.

100% Circular Zero Compromise on Performance



Interested in including Dramix® Loop™ in your next project?

We are looking for likeminded pioneers to implement this innovative solution. Our team of concrete reinforcement experts is ready to support you with a tailored implementation plan - from concept to completion.

Contact our team of concrete reinforcement experts:

Visit [construction.bekaert.com](https://www.construction.bekaert.com) or email infobuilding@bekaert.com

[construction.bekaert.com](https://www.construction.bekaert.com) →

Bekaertstraat 2
8550 Zwevegem, BELGIUM

Modifications reserved. All details describe our products in general form only. For ordering and design only use official specifications and documents. Unless otherwise indicated, all trademarks mentioned in this brochure are registered trademarks of NV Bekaert SA or its subsidiaries. © Bekaert 2025
Responsible editor: NV Bekaert SA - 07 2025

Dense fibre network, low dosages

Dramix® Loop™ steel fibres offer a high tensile strength of 2.700 MPa avg., while their diameter of 0,27 mm avg. makes it possible to achieve a denser fibre network. This, in turn, allows for lower fibre dosages per cubic meter of concrete. Dramix® Loop™ 20 and 25 steel fibres are CE marked, conform with EAD 260010-00-0301 and ETA 25/0711.

Description	Dramix® Loop™ 15	Dramix® Loop™ 20	Dramix® Loop™ 25
Geometry	Random	Random	Random
Average length	15 mm	20 mm	25 mm
Average diameter	0,27 mm	0,27 mm	0,27 mm
Aspect ratio	55	75	93
Average tensile strength (MPa)	2.700 MPa	2.700 MPa	2.700 MPa
Average number of fibers per kg	160.000	120.000	96.000
Dosage per m ³	3 - 80 kg/m ³	3 - 80 kg/m ³	3 - 80 kg/m ³
EPD value	0,0436	0,0436	0,0436

* All mentioned values are indicative

Maximizing performance, minimizing environmental impact



Near-zero carbon emissions: Dramix® Loop™ is made from second life steel, significantly reducing its environmental impact, as it has an EPD value of 0,0436 kg CO₂e/kg.



Ultra dense fibre network: Thanks to the fibres' high aspect ratio, a count of up to 160.000 fibres/kg avg. within the concrete matrix can be achieved. This leads to enhanced crack control and post-cracking ductility, while the high tensile strength ensures that steel fibres can withstand high stress without breaking.



Driving a circular economy: Made from the tyre cord of end-of-life tyres, Dramix® Loop™ repurposes steel to reduce landfill waste, conserve valuable resources, and support a sustainable, closed-loop economy.



Maximized benefits of steel fibre reinforcement: Dramix® Loop™ delivers all the advantages of conventional steel fibres - cost-efficiency, enhanced durability, and improved safety - while offering the added benefit of sustainability.

The ideal solution for a wide range of concrete applications

- Industrial floors
- Outdoor pavements
- Residential applications
- Sprayed concrete
- Infrastructure applications
- Precast elements
- (Ultra) High Performance Concrete (UHPC/HPC)